

Product Details

Color:	Gray	Size:	1 KG
Material:	Acrylate-based Polymer for 3D Printing	Tensile(MPa):	62 - 68
Elongation(%):	3-7	Impact(J/m):	27-33
Hardness(Shore):	91-93D	Flexural Strength(MPa):	114-118
Flexural Modulus(MPa):	1980-2050	HDT(°F/°C):	161.8°F/72.1°C
Tear Strength(kN/m):	-	Compression(%):	-
Viscosity at 77°F/25°C:	550-660	Layer thickness(um):	0.1 mm
PostCure method:	FormCure 60°C, 60min		